

## TECHNICAL DATA SHEET

### Endur® 1100 GF10

Endur® 1100 GF10 is a general purpose, 10% glass reinforced polybutylene terephthalate with a good balance of mechanical properties and processability.

Properties	Test method	Unit	Value
Contents of reinforcement materials	-	%	10
Density	ISO 1183	g/cm <sup>3</sup>	1,38
Melt volume flow rate (205°C/2,16kg)	ISO 1133	cm <sup>3</sup> /10 min	22
Viscosity number	ISO 1628-5	cm <sup>3</sup> /g	120
Waterabsorption up to saturation (23°C)	ISO 62	%	0,4
Moisture absorption (24h 23°C)	ISO 62	%	0,2
Molding shrinkage (longitudinal) (260°C/WZ 80°C)	ISO 2577	%	0,8
Molding shrinkage (transverse) (600 bar)	ISO 2577	%	1,4
Tensile modulus (1 mm/min)	ISO 527	MPa	4800
Stress at break (5 mm/min)	ISO 527	MPa	100
Strain at break (5 mm/min)	ISO 527	%	4
Flexural modulus (2 mm/min)	ISO 178	MPa	4300
Flexural strength (2 mm/min)	ISO 178	MPa	150
Flexural strain at flexural strength (2 mm/min)	ISO 178	%	5
Flexural stress at 3,5% strain (2 mm/min)	ISO 178	MPa	135

## TECHNICAL DATA SHEET

### Endur® 1100 GF10

Properties	Test method	Unit	Value
Charpy impact strength (23°C)	ISO 179-1eU	kJ/m <sup>2</sup>	35
Charpy impact strength (-30°C)	ISO 179-1eU	kJ/m <sup>2</sup>	30
Charpy notched impact strength (23°C)	ISO 179-1eA	kJ/m <sup>2</sup>	5
Charpy notched impact strength (-30°C)	ISO 179-1eA	kJ/m <sup>2</sup>	4
Ball indentation (358 N)	ISO 2039-1	N/mm <sup>2</sup>	160
Melting temperature (10°C/min)	ISO 11357	°C	220 - 225
Temp. of deflection under load (HDT A) (1,80 MPa)	ISO 75	°C	190
Temp. of deflection under load (HDT B) (0,45 MPa)	ISO 75	°C	210
Temp. of deflection under load (HDT C) (8,00 MPa)	ISO 75	°C	60
Vicat softening temperature (50 N, 50°C/h)	ISO 306	°C	205
Coeff. of linear therm. expansion (longitudinal)	ISO 11359	10 <sup>-4</sup> /k	0,5
Coeff. of linear therm. expansion (transverse)	ISO 11359	10 <sup>-4</sup> /k	1,1
Flammability test (0,80 mm)	TC	Klasse / Classifcat.	HB
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	°C	750